













Dati tecnici secondo norme: Technical data conform to: Caractéristiques techniques d'après normes: Technische Daten nach den Normen: EN 14411 Bia GL			APPROACH	APPROACH OUT	APPROACH LAPP
	Caratteristiche Tecniche Technical Data Caractéristiques Techniques Tecniche Daten	Norme Normes Normes Norm	Valori Value Valeur Wert	Valori Value Valeur Wert	Valori Value Valeur Wert
	Resistenza all'abrasione Abrasion resistance Résistance à l'abrasion Abrasionswiderstandigkeit	ISO 10545 - 7	PEI V	PEI IV	PEI IV
	Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	ISO 10545 - 3	≤ 0,1%	≤ 0,1%	≤ 0,1%
	Resistenza alla flessione Breaking modulus Résistance à la flexion Biegefestigkeit	ISO 10545 - 4	40=55 N/mm ²	40=55 N/mm ²	40=55 N/mm ²
	Resistenza al gelo Resistance to frost Résistance au gel Frostbeständigkeit	ISO 10545 - 12	NON GELIVE FROST PROOF INGELIF FROSTSICHER	NON GELIVE FROST PROOF INGELIF FROSTSICHER	NON GELIVE FROST PROOF INGELIF FROSTSICHER
	Resistenza all'attacco acido e basico Glaze resistance to acid and alkaline attack Résistance aux acides et aux bases Saeure-und laugenfestigkeit	ISO 10545 - 13	RESISTE RESISTS RESISTE BESTÄNDIG	RESISTE RESISTS RESISTE BESTÄNDIG	RESISTE RESISTS RESISTE BESTÄNDIG
	Durezza Mohs Mohs hardness Dureté Mohs Haerte Mohs	EN101	8	9	-
	Resistenza alle macchie Stain resistance Résistance aux taches Fleckenfestigkeit	ISO 10545 - 14	TOTALE COMPLETE TOTALE ABSOLUT	TOTALE COMPLETE TOTALE ABSOLUT	TOTALE COMPLETE TOTALE ABSOLUT
	Scivolosità Slipperiness Degré de glissement Rutschhemmung	DIN 51130	R10	R11	
	Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschhemmung	DIN 51097	B	C	-
	Scivolosità Coefficient of friction Degré de glissement Rutschhemmung	ANSI A137-1	> 0,42	> 0,42	-
	Scivolamento B.C.R.A. Slipperiness B.C.R.A. Degré de glissement B.C.R.A. Rutschhemmung B.C.R.A.	TORTUS	> 0,40	> 0,40	-
ASTM	Scivolosità Coefficient of friction Degré de glissement Rutschhemmung	ASTM C1028	> 0,60	> 0,60	-
	Stonalizzazione Shading Denuançage Spielfarbig	-	V3	V3	V3

I valori indicati nella tabella si riferiscono alle prove eseguite sul colore TAUPE.

The values in the table refer to the tests performed on color TAUPE.

Les valeurs indiquées dans le tableau se réfèrent aux essais exécutés sur le couleur TAUPE.

Die in der Tabelle angegebenen Werte beziehen sich auf die Tests die auf dem Farbe TAUPE ausgeführt wurden.

Los valores indicados en la tabla se refieren a las pruebas realizadas sobre el color TAUPE.

Указанные в таблице значения относятся к испытаниям, проведенным на бежевом оттенке TAUPE.